



MATBOCK Ghost

Proprietary composite fabric with Multicam®

FEATURES

- 70D Ripstop Multicam® fabric on front and back
- Proprietary composite reinforcement
- High tear strength and very low stretch
- Waterproof
- Berry Amendment Compliant

Typical Properties of MATBOCK Ghost

Dimensions ⁽¹⁾	Value	Unit
Usable Roll Width	54 (1.37)	in (m)
Roll Length	29.5 (9)	ft (m)

Typical Properties ⁽¹⁾		Value	Unit	Standard
Weight		11.8 (400)	oz/yd ² (g/m ²)	ASTM D3776
Failure Strength	Wrap	460 (2000)	lbf/in (N/25mm)	ASTM D3039
	Fill	460 (2000)		
Strain at Failure	Wrap	2.6	%	ASTM D3039
	Fill	2.6		
Modulus	Wrap	20000 (88000)	lbf/in (N/25mm)	ASTM D3039
	Fill	20000 (88000)		
Slit Tear Strength (max)	Wrap	250 (1100)	lbf (N)	Mil-C-21189 10.2.4
	Fill	250 (1100)		
Puncture Resistance		31 (140)	lbf (N)	ASTM F1342 (Probe B)

⁽¹⁾ Actual Properties of individual batches will vary; values listed in table are average values or estimates

WARRANTY: OTHER THAN REPLACING PRODUCTS NOT MEETING A FULLY EXECUTED SPECIFICATION PRIOR TO ANY PROCESSING (SPECIFICATION INVALID IF NOT SIGNED BY CUSTOMER AND MATBOCK), MATBOCK ASSUMES NO LIABILITY WHATSOEVER WITH RESPECT TO APPLICATION, PROCESSING, RESALE OR OTHER USE OF PRODUCTS SUPPLIED. BUYER SHOULD PERFORM ITS OWN TESTING AND ANALYSIS TO DETERMINE THE SUITABILITY OF MATBOCK PRODUCTS FOR ITS SPECIFIC APPLICATIONS. NO LIABILITY WHATSOEVER SHALL ATTACH TO MATBOCK. FOR ANY INFRINGEMENT OF THE RIGHTS OWNED OR CONTROLLED BY A THIRD PARTY IN INTELLECTUAL, INDUSTRIAL OR OTHER PROPERTY BY REASON OF THE APPLICATION, PROCESSING OR USE OF PRODUCTS BY THE BUYER.

MATBOCK

1164 Millers LN Suite D
Voice: 757-828-6659

Virginia Beach, VA 23455



MATBOCK Ghost Lite

Proprietary composite fabric with Multicam®

FEATURES

- 6.0 oz/yd²
- 70D Ripstop Multicam® fabric on the front
- Proprietary composite reinforcement
- Very low stretch in fiber reinforced directions
- Abrasion resistant lightweight woven face fabric and back waterproof surface coating
- Waterproof & Low Moisture Absorption
- Berry Amendment Compliant

Typical Properties of MATBOCK Ghost Lite

Dimensions ⁽¹⁾	Value	Unit
Usable Roll Width	54 (1.37)	in (m)
Roll Length (folds every 9m)	59 (18)	ft (m)

Typical Properties ⁽¹⁾	Value	Unit	Standard
Weight	6 (240)	oz/yd ² (g/m ²)	ASTM D3776
Failure Strength	264 (46)	lbf/in (kN/m)	ASTM D3039
Strain at Failure	2.9	%	ASTM D3039
Modulus	8,640 (1,513)	lbf/in (kN/m)	ASTM D3039
Slit Tear Strength (First Peak)	110 (489)	lbf (N)	Mil-C-21189 10.2.4
Puncture Resistance	12.5 (55)	lbf (N)	ASTM F1342 (Probe B)
Hydrostatic Pressure Resistance	>20000	mm H ₂ O	AATCC TM127

⁽¹⁾ Actual Properties of individual batches will vary; values listed in table are average values or estimates

WARRANTY: OTHER THAN REPLACING PRODUCTS NOT MEETING A FULLY EXECUTED SPECIFICATION PRIOR TO ANY PROCESSING (SPECIFICATION INVALID IF NOT SIGNED BY CUSTOMER AND MATBOCK), MATBOCK ASSUMES NO LIABILITY WHATSOEVER WITH RESPECT TO APPLICATION, PROCESSING, RESALE OR OTHER USE OF PRODUCTS SUPPLIED. BUYER SHOULD PERFORM ITS OWN TESTING AND ANALYSIS TO DETERMINE THE SUITABILITY OF MATBOCK PRODUCTS FOR ITS SPECIFIC APPLICATIONS. NO LIABILITY WHATSOEVER SHALL ATTACH TO MATBOCK. FOR ANY INFRINGEMENT OF THE RIGHTS OWNED OR CONTROLLED BY A THIRD PARTY IN INTELLECTUAL, INDUSTRIAL OR OTHER PROPERTY BY REASON OF THE APPLICATION, PROCESSING OR USE OF PRODUCTS BY THE BUYER.